



TECHNICAL DATA SHEET – MS-7CZ

Revised:08/2023

THE STANDARD PRIMER FOR PRESERVING STEEL

PRODUCT DESCRIPTION

AST MS-7CZ RUST INHIBITIVE PRIMER is a lead and chromate free, rust inhibitive, two-component, epoxy primer specifically designed for use in conjunction with Holcim Solutions and Products US, LLC' coatings applied to metal substrates. It meets USDA standards for maintenance protective coatings not in direct contact with food in federally inspected meat and poultry plants.

USE & BENEFITS

AST MS-7CZ RUST INHIBITIVE PRIMER is recommended for use as a metal primer in severe industrial and chemical environments. It possesses excellent adhesion to properly prepared iron and steel surfaces, providing rust resistance to ferrous substrates, both on initial application and in the event of damage to the topcoat. It can be used under many epoxy, urethane, vinyl, chlorinated rubber and coal tar/epoxy finish coats.

The 7CZ Primer contains a new, state-of-the-art compound that was created by combining zinc and phosphate at the molecular level. Zinc complexed with phosphate becomes a non-metallic compound that is completely different, from regular, inorganic zinc. Inorganic zinc primers are made from ground metallic zinc powder mixed with a very basic inorganic polymeric liquid. Rust Inhibitive 7CZ Primer, on the other hand, is made up of a very high quality, 2-component, polyamide epoxy and a small amount of zinc complexed with phosphate. Rather than metallic zinc, the 7CZ Primer has very good anticorrosion properties and promotes adhesion of steel to epoxy grout.

SURFACE PREPARATION

Steel: Surfaces must be dry, clean and free of all previous coatings, rust and surface contamination. Minimum surface preparation is abrasive blast to Commercial Grade SP-6. Blasted surfaces must be coated within 8 hours. Prior to blast cleaning, remove all deposits of oil or grease using Solvent Clean method SP-1.

Previously Painted Surfaces: If the paint is peeling or degrading in any way, it should be completely removed by sanding, blasting or stripping. If previous paint coating is completely intact, the surface may be cleaned with a strong detergent or solvent and scuff sanded to remove the gloss. A spot test should be made by applying a small amount of coating over old paint. The old finish may wrinkle or lift within 60 minutes. If it does not, wait 5 days and test for adhesion. Do this by cutting an "X" into the coating, place tape firmly over the cut, then pull the tape with a hard, fast pull. If the old finish fails, it must be removed.

MS-7CZ

ANTI-CORROSIVE LOW V.O.C. METAL PRIMER
MIL-PRF-24667C

APPLICATION INSTRUCTIONS

- Applications should only take place when material, surface, and ambient temperature are all above 55°F (13°C) and at least 5°F (3°C) above the dew point. Application not recommended with surface temperatures over 120°F (49°C).
- AST MS-7CZ RUST INHIBITIVE PRIMER should be applied to a minimum 2-3 mils (50-75 microns) dry film thickness above the averaged surface profile and a maximum of 6 mils (152 microns) DFT.
- AST MS-7CZ RUST INHIBITIVE PRIMER can be applied by spray, roller or brush. Spraying should be done perpendicular to the surface to insure complete coverage. Each pass of the spray gun should overlap the previous pass by 50%. Weld seams and edges should be stripe coated prior to complete prime coat.
- AST MS-7CZ RUST INHIBITIVE PRIMER is a two-part compound. Mechanically mix the base portion until homogenous. Pour the hardener into the container of base material and mechanically stir thoroughly until uniform (approximately three minutes). NO THINNERS MAY BE ADDED. Make sure that all sediment is stirred up off the bottom of the can.
- AST MS-7CZ RUST INHIBITIVE PRIMER does not require the usual induction period and may be applied immediately after mixing. Working pot life is 4 hours at 70°F.
- The primed surface should be protected from contamination.
- If the top coat or grout application is delayed so that the surface becomes contaminated, clean the area again.
- Clean tools and spray equipment immediately after completing installation using an epoxy solvent compliant with state and federal V.O.C. regulations.

PHYSICAL PROPERTIES

| | |
|-------------------|--|
| COLOR | Gray, Buff or Light Gray |
| VOLUME SOLIDS - % | 72% |
| POT LIFE | 4 hours @ 70°F (21°C) |
| DRY TIME | Tack Free –2 hours @ 70°F (21°C) To Recoat - 12 hours @ 70°F (21°C) |

PRODUCT SPECIFICATIONS

| | |
|-------------------------|--|
| COVERAGE | 250 sq. ft./gal. (4 mils DFT / 6.5 mils WFT) |
| APPLICATION TEMPERATURE | 55°F minimum to 120°F maximum + (13°C minimum to 48°C maximum +) 5°F (3°C) above dew point |
| SHELF LIFE | 12 months |
| RELATIVE HUMIDITY | 85% maximum |
| REDUCER | None |
| CLEAN UP | S-426, S-31, Solvents, Isopropyl Alcohol, MAK Solvent |
| WEIGHT PER GALLON | 12.6 lbs. per gal. (1.52 kg./liter) |
| UNIT PACKAGING | Resin (NH): 2.9 L (0.77 gal) in a 1 gal can Hardener (NH): 0.87 L (0.23 gal) in a quart can |
| UNIT WEIGHT | Resin: 4.9 kg (10.8 lbs) Hardener: 0.86 kg (1.9 lbs) |

American Safety Technologies is a ® Registered Trademark of Holcim Solutions and Products US, LLC. © Copyright 2023 Holcim Solutions and Products US, LLC. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.holcimast.com for the most current technical data and instructions. Or you may contact your Holcim representative for current technical data and instructions. EXCLUSION OF WARRANTIES: INSTALL AS DIRECTED ON AMERICAN SAFETY TECHNOLOGIES PRODUCT DATA SHEET. USER DETERMINES SUITABILITY FOR INTENDED USE AND ASSUMES ALL RISK AND LIABILITY. THIS PRODUCT IS SOLD "AS IS". EXCEPT AS REQUIRED BY LAW, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. IF TERMS ARE NOT ACCEPTABLE, RETURN UNOPENED PRODUCT TO PLACE OF PURCHASE.